

<b>Group</b>	<b>Subgroup</b>	<b>% Passing 0.075 mm Sieve</b>	<b>Plasticity Index</b>	<b>CON-AID Application Rate (liter/m<sup>2</sup>)</b>	<b>Purpose of CON-AID Products</b>
A-1	A-1-a	15 max	6 max	0.01	Facilitate compaction
	A-1-b	25 max	6 max	0.01	Stabilize fines
A-2	A-2-4	35 max	10 max	0.01	Facilitate compaction
	A-2-5	35 max	10 max	0.015	Stabilize silt fines
	A-2-6	35 max	11 min	0.015	Stabilize clay fines
	A-2-7	35 max	11 min	0.020	Increase CBR
A-3		10 max	Non-Plastic	N/A	N/A
A-4		36 min	10 max	0.020	Facilitate compaction
A-5		36 min	10 max	0.025	Stabilize silts Stabilize clays
A-6		36 min	11 min	0.02 – 0.03	Stabilize silty clays
A-7	A-7-5	36 min	11 min	0.02 - 0.03	Increase CBR
	A-7-6	36 min	11 min	0.02 - 0.03	Improve Workability
A-8				N/A	N/A

NOTE: This is only a rough guideline of soil workability with CON-AID, for more information, please kindly contact us [info@conaidasia.com](mailto:info@conaidasia.com)